Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 21/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 25-11-19

: Drain Side Wall Concrete

: 150X150X150 mm

: M20 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 21/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	23/11/2019	21/12/2019	149.53 X 151.46 X 149.23	22648	**8.185**	524.8	23.2	22.9
Drain Side Wall Concrete	M20	23/11/2019	21/12/2019	150.17 X 150.38 X 151.05	22581	**8.804**	502.6	22.3	
Drain Side Wall Concrete	M20	23/11/2019	21/12/2019	150.22 X 150.82 X 151.40	22656	**8.147**	528.2	23.3	

18/2/2020

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 03/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 28-11-19

: Drain Side Wall Concrete

: 150X150X150 mm

: M20 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 03/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	151.30 X 149.33 X 150.35	22593	**8.841**	428.8	19.0	18.7
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	151.76 X 151.76 X 150.33	23031	**8.681**	418.5	18.2	
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	150.29 X 151.86 X 150.93	22822	**8.639**	430.7	18.9	

18/12/2020

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 24/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 28-11-19

: Drain Side Wall Concrete

Size : 150X150X150 mm

Age : M20 / 28 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 24/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	149.17 X 149.17 X 151.60	22252	**8.185**	533.2	24.0	23.1
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	151.74 X 149.30 X 151.99	22655	**8.804**	505.5	22.3	
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	150.71 X 149.22 X 149.04	22490	**8.147**	517.3	23.0	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 03/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 28-11-19

: Drain Side Wall Concrete

Size : 150X150X150 mm

Age : M20 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 03/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	151.20 X 151.24 X 151.96	22868	**8.841**	431.5	18.9	18.5
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	151.84 X 151.00 X 150.32	22928	**8.681**	416.3	18.2	
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	151.78 X 150.18 X 150.55	22794	**8.639**	417.8	18.3	

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 24/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 28-11-19

: Drain Side Wall Concrete

Size : 150X150X150 mm

Age : M20 / 28 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 24/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	150.24 X 150.19 X 149.62	22566	**8.185**	529.2	23.5	23.2
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	151.10 X 150.18 X 151.74	22693	**8.804**	503.7	22.2	
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	150.90 X 149.07 X 151.09	22495	**8.147**	537.1	23.9	

CIVIL PRO Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 03/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 28-11-19

: Drain Side Wall Concrete

Size : 150X150X150 mm

Age : M20 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 03/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	150.45 X 149.36 X 151.47	22471	**8.841**	412.8	18.4	18.6
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	151.24 X 151.00 X 149.43	22838	**8.681**	428.1	18.7	
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	149.89 X 151.59 X 150.15	22721	**8.639**	421.2	18.5	

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

2924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 24/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

Receipt : 28-11-19

ID : Drain Side Wall Concrete

Type /Size : 150X150X150 mm

Grade/Age : M20 / 28 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 24/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	150.88 X 151.05 X 149.13	22791	**8.185**	545.4	23.9	23.3
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	151.79 X 149.01 X 151.16	22618	**8.804**	502.2	22.2	
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	149.46 X 149.47 X 149.06	22339	**8.147**	528.3	23.7	

18/2/2020

FOR CIVIL Pro.

Sig.....
Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 03/12/2019

: CP-2020-01-30-84

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 28-11-19

: Drain Side Wall Concrete

Size : 150X150X150 mm

Age : M20 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 03/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	151.64 X 150.45 X 150.30	22814	8.841	433.1	19.0	18.8
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	150.93 X 149.61 X 149.96	22580	8.681	426.2	18.9	
Drain Side Wall Concrete	M20	26/11/2019	03/12/2019	150.77 X 149.51 X 150.71	22542	8.639	415.6	18.4	

19/2/2020

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 24/12/2019

: CP-2020-01-30-84

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

: EE(Project)/Ynk Zone/WO/65/2019-20

: 28-11-19

: Drain Side Wall Concrete

: 150X150X150 mm

: M20 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 24/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	151.66 X 150.30 X 149.08	22795	8.185	529.7	23.2	23.1
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	149.50 X 149.13 X 149.63	22295	8.804	507.5	22.8	
Drain Side Wall Concrete	M20	26/11/2019	24/12/2019	151.54 X 151.59 X 150.11	22972	8.147	535.0	23.3	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 09/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 04-12-19

: Drain Side Filling Concrete

Size : 150X150X150 mm

Age : M20 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 09/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Filling Concrete	M20	02/12/2019	09/12/2019	149.85 X 151.96 X 150.61	22771	**8.841**	411.9	18.1	18.5
Drain Side Filling Concrete	M20	02/12/2019	09/12/2019	151.49 X 149.79 X 151.48	22693	**8.681**	429.6	18.9	
Drain Side Filling Concrete	M20	02/12/2019	09/12/2019	149.75 X 151.95 X 149.35	22753	**8.639**	423.1	18.6	

13/2/2020

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 30/12/2019

: CP-2020-01-30-84

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 04-12-19

: Drain Side Filling Concrete

Type /Size : 150X150X150 mm

grade/Age : M20 / 28 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 30/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Filling Concrete	M20	02/12/2019	30/12/2019	151.41 X 150.67 X 150.94	22814	**8.185**	542.6	23.8	23.0
Drain Side Filling Concrete	M20	02/12/2019	30/12/2019	151.81 X 151.26 X 150.44	22963	**8.804**	512.4	22.3	
Drain Side Filling Concrete	M20	02/12/2019	30/12/2019	149.73 X 150.94 X 151.61	22600	**8.147**	520.7	23.0	

18/2/2020

CIVIL PRO Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 09/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 04-12-19

: Drain Side Filling Concrete

Size : 150X150X150 mm

Age : M20 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 09/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Filling Concrete	M20	02/12/2019	09/12/2019	149.55 X 150.51 X 151.21	22509	8.841	422.8	18.8	18.8
Drain Side Filling Concrete	M20	02/12/2019	09/12/2019	149.09 X 149.55 X 150.64	22296	8.681	420.9	18.9	
Drain Side Filling Concrete	M20	02/12/2019	09/12/2019	149.14 X 150.36 X 151.37	22425	8.639	423.4	18.9	

18/2/2020

FOR CIVIL Pro.

Sig.....
Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-01-30-84** **Date: 30/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

Receipt : 04-12-19

ID : Drain Side Filling Concrete

Type /Size : 150X150X150 mm

Grade/Age : M20 / 28 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 30/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Filling Concrete	M20	02/12/2019	30/12/2019	150.29 X 149.83 X 149.57	22518	8.185	529.1	23.5	23.1
Drain Side Filling Concrete	M20	02/12/2019	30/12/2019	151.41 X 150.97 X 151.49	22858	8.804	512.4	22.4	
Drain Side Filling Concrete	M20	02/12/2019	30/12/2019	151.09 X 150.71 X 151.59	22772	8.147	529.8	23.3	

18/2/2020

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 09/12/2019

: CP-2020-01-30-84

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

: 04-12-19

: Drain Side Filling Concrete

/Size : 150X150X150 mm

/Age : M20 / 7 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 09/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Filling Concrete	M20	02/12/2019	09/12/2019	149.38 X 150.16 X 150.34	22431	8.841	415.9	18.5	18.3
Drain Side Filling Concrete	M20	02/12/2019	09/12/2019	150.94 X 151.14 X 151.89	22812	8.681	415.8	18.2	
Drain Side Filling Concrete	M20	02/12/2019	09/12/2019	149.63 X 150.28 X 149.08	22487	8.639	405.4	18.0	

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

18/2/2020

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-01-30-84 **Date: 30/12/2019**

: Improvements CC Road and Drain and Slabs at Kattigenahalli in Ward No.05 Byatarayanapura Sub Division

: Executive Engineer, KRIDL, Bangalore.

Reference : EE(Project)/Ynk Zone/WO/65/2019-20

Receipt : 04-12-19

ID : Drain Side Filling Concrete

Type /Size : 150X150X150 mm

grade/Age : M20 / 28 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 30/12/2019

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Drain Side Filling Concrete	M20	02/12/2019	30/12/2019	151.85 X 150.97 X 150.00	22926	**8.185**	544.5	23.8	23.4
Drain Side Filling Concrete	M20	02/12/2019	30/12/2019	151.92 X 150.63 X 151.64	22884	**8.804**	516.8	22.6	
Drain Side Filling Concrete	M20	02/12/2019	30/12/2019	149.12 X 151.55 X 150.23	22598	**8.147**	539.0	23.9	

18/2/20

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com